



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 908 500 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

14.04.1999 Bulletin 1999/15

(51) Int Cl.⁶: **C09K 3/18, C03C 17/28**

(21) Application number: **98308280.1**

(22) Date of filing: **12.10.1998**

(84) Designated Contracting States:

**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**

Designated Extension States:

AL LT LV MK RO SI

(30) Priority: **13.10.1997 JP 279012/97**

(71) Applicants:

- **CANON KABUSHIKI KAISHA**
Tokyo (JP)
- **Nakato Laboratory, Inc.**
Yasu-gun, Shiga-ken (JP)

(72) Inventors:

- **Ikemori, Keiji**
Tokyo (JP)

• **Ohtaka, Keiji**

Tokyo (JP)

• **Ukuda, Hideo**

Tokyo (JP)

• **Yamamoto, Tohru**

Yasu-gun, Shiga-ken (JP)

• **Yoshida, Shigeo**

Yasu-gun, Shiga-ken (JP)

• **Ikari, Hatsumi**

Yasu-gun, Shiga-ken (JP)

(74) Representative:

Beresford, Keith Denis Lewis et al

BERESFORD & Co.

2-5 Warwick Court

High Holborn

London WC1R 5DJ (GB)

(54) **Anti-fog coating material and anti-fog article**

(57) An anti-fog article is obtained by coating a substrate with an anti-fog coating material to form thereon an anti-fog coating film that is hydrophilic, moisture-ab-

sorptive, insoluble and excellent in surface hardness. The anti-fog coating material contains a polyacrylic acid compound, polyvinyl alcohol and acetylacetone, and optionally sodium silicate.

1, 2, 4, 5, 7, 10, 11

EP 0 908 500 A1

Description**FIELD OF THE INVENTION AND RELATED ART**

5 [0001] The present invention relates to an anti-fog coating material capable of forming an insoluble coating film having a high surface hardness and a hydrophilicity and moisture absorptivity-imparting function onto substrates, such as optical lenses, spectacles and window panels for vehicles expected to show anti-fog property and anti-(moisture) condensation property, and ink jet printer recording films, and also to an anti-fog article provide with an anti-fog coating film formed by using such an anti-fog coating material.

10 [0002] A substrate, such as that of glass or a plastic, may become foggy when the surface temperature thereof is cooled to below a dew point of atmospheric air, and atmospheric moisture is attached to the surface in the form of fine droplets to cause random reflection of light incident to the substrate surface. Accordingly, it may be possible to prevent the fog on the substrate by preventing such moisture droplet formation on the substrate surface. In such a fog-preventing method, for example, four measures of (A) adjustment of wettability, (B) provision of moisture absorptivity, (C) provision of water repellency and (D) moisture adjustment by heating, have been considered.

15 [0003] The measure (A) as by use of a surface active agent cannot provide a long lasting effect.

[0004] The effect given by the measure (B) lasts for a longer period than that given by (A), but fog is liable to occur and the surface is liable to be dissolved when the moisture exceeds the moisture-absorptive capacity.

20 [0005] The measure (C) provides the anti-fog property by causing water droplets to fall off the surface due to the water repellency of the surface, but cannot cope with fine water droplets.

[0006] The measure (D) provides the anti-fog effect owing to moisture adjustment by heating, but the scope of application thereof is restricted by the necessity of an electric power supply.

SUMMARY OF THE INVENTION

25 [0007] In view of the above-mentioned problems, an object of the present invention is to provide a coating material for providing an anti-fog coating film that is hydrophilic, moisture-absorptive and insoluble and also has an excellent surface hardness.

30 [0008] Another object of the present invention is to provide an anti-fog article provided with an anti-fog coating film formed by using such an anti-fog coating material.

[0009] According to the present invention, there is provided an anti-fog coating material or composition, comprising: a polyacrylic acid compound, polyvinyl alcohol and acetylacetone. The coating material may further contain sodium silicate.

35 [0010] According to another aspect of the present invention, there is provided an anti-fog article, comprising: a substrate and a coating film formed on the substrate by application of a solution containing a polyacrylic acid compound, polyvinyl alcohol and acetylacetone.

40 [0011] An anti-fog coating film formed of the anti-fog coating material of the present invention is water-insoluble, and has a high surface hardness and excellent durability. Such properties may be attributable to an improved mutual solubility between the polyacrylic acid compound and the polyvinyl alcohol accomplished by the presence of acetylacetone therebetween. More specifically, a polyacrylic acid compound and polyvinyl alcohol have poor mutual solubility therebetween but are both well dissolved together with acetylacetone to form a uniform coating film. The coating film is hard, excellent in durability and water-insoluble. This is presumably because the improved mutual solubility between the polyacrylic acid compound and polyvinyl alcohol promotes mutual interaction of polymer chains of these compounds to provide an insoluble coating film, wherein the acetylacetone is retained presumably in a state of chemically bonded with the polyacrylic acid compound and the polyvinyl alcohol.

DETAILED DESCRIPTION OF THE INVENTION

50 [0012] Preferred examples of the polyacrylic acid compound may include: polyacrylic acid, polymethacrylic acid, and lower alkyl (C1 - C4) esters, particularly methyl and ethyl esters, respectively, of acrylic acid and methacrylic acid. It is preferred that the alkyl esters of polyacrylic acid and polymethacrylic acid respectively have a saponification degree (i.e., mols of hydrolyzed ester groups x 100/(mols of hydrolyzed ester groups + mols of non-hydrolyzed ester groups) of 10 - 30 mol. %. The polyacrylic acid compound may preferably have a weight-average molecular weight (Mw) of 50,000 - 350,000 in terms of polystyrene-equivalent molecular weight according to gel permeation chromatography (GPC).

55 [0013] The polyvinyl alcohol used in the present invention may preferably be in the form of a partially or incompletely saponified product of polyvinyl acetate that has a polymerization degree (Dp) of at least 1,000, is soluble in an organic solvent and has a saponification degree (i.e., mols of hydroxyl group x 100/(mols of acetyl group + mols of hydroxyl

group) of 65 - 85 mol. %, more preferably 75 - 82 mol. %. The polyvinyl alcohol may preferably be used in an amount of 100 - 1000 wt. parts (as solid) per 100 wt. parts (as solid) of the polyacrylic acid compound.

[0014] Acetylacetone may be used in the coating material of the present invention before the application thereof in an amount of 3 - 50 wt. parts per 100 wt. parts (as solid) of the total of the polyacrylic acid compound and the polyvinyl alcohol.

[0015] The anti-fog coating material according to the present invention before the application thereof may preferably be in the form of a solution in an organic solvent, which may preferably be a water-miscible organic solvent, such as methyl alcohol, ethyl alcohol or isopropyl alcohol. The organic solvent may further preferably be used in combination with water. The preferred ratio of the organic solvent to water may be different depending on the particular solvent used, e.g., 80 - 120 wt. parts of methyl alcohol or ethyl alcohol, or 40 - 80 wt. parts of isopropyl alcohol, respectively, per 100 wt. parts of water.

[0016] The anti-fog coating material according to the present invention may further preferably contain sodium silicate, which may preferably have an $\text{SiO}_2/\text{Na}_2\text{O}$ mol ratio of 2.1 - 3.1. The sodium silicate may preferably be used in 0.5 - 10 wt. parts (as solid) per 100 wt. parts (as solid) of the total of the polyacrylic acid compound and the polyvinyl alcohol.

[0017] The anti-fog coating material according to the present invention may be used to coat a substrate, examples of which may include: glass articles and plastic articles, such as, lenses, optical parallel plates, and mirrors, prisms.

[0018] The anti-fog article according to the present invention may for example be prepared in the following manner. The above-mentioned respective components of the anti-fog coating material are blended to form a clear coating liquid. Then, the coating liquid is applied onto at least one surface of a substrate as described above and dried under heating at a temperature of at least 80 °C, preferably 120 - 200 °C, to provide an anti-fog article of the present invention. The above coating liquid application may be repeated several times, as desired, to provide an increased thickness of the coating film, with or without heating after each application. The heating may also be performed after several times of application.

[0019] The color film may preferably have a thickness of 0.01 μm - 1.0 μm , e.g., for optical lenses, and 1.0 μm - 10.0 μm , e.g., for window panels. The coating film thickness may be adjusted appropriately by applying a thick layer of the coating liquid or by repeatedly applying the coating liquid in superposition.

[0020] The thus-prepared anti-static article may have a surface provided with anti-fog property and anti-condensation property. The resultant anti-fog coating film is insoluble in water and organic solvent and exhibits a high surface hardness.

[0021] In a preferred embodiment of preparation of the anti-fog coating material according to the present invention, the polyacrylic acid compound and polyvinyl alcohol are dissolved in a solvent mixture of a lower alcohol, as an organic solvent, and water, and acetylacetone is added to form a uniform coating mixture liquid, which may be dried to provide a uniform film layer through uniform drying without exceeding mutual solubility-separation limit during the film formation step owing to the function of the acetylacetone.

[0022] In another preferred embodiment of preparation of the anti-fog coating material according to the present invention, the polyacrylic acid compound, polyvinyl alcohol and sodium silicate are blended and dissolved in a solvent mixture of a lower alcohol and water, followed by addition of acetylacetone to form a uniform coating mixture liquid, which may be dried while precipitating SiO_2 due to hydrolysis of the sodium silicate to provide a uniform film layer through uniform drying without exceeding mutual solubility-separation limit during the film formation step owing to the function of the acetylacetone. The sodium silicate may be contained in the resultant coating film in its hydrolyzed form.

[Examples]

[0023] Hereinbelow, the present invention will be described more specifically based on Examples.

Example 1

[0024]

(Table 1)

Polymethylmethacrylate 20 mol. %-saponified product ($\text{Mw} = 15 \times 10^4$) (2.3 wt. % solution in water/methanol (= 100/100 by weight))	52.0 wt. parts
Polyvinyl alcohol 10 wt. %-aqueous solution ($\text{Dp} = 2000$, ca. 82 mol. %-saponified product)	47.1 wt. parts
Acetylacetone	0.9 wt. part
Total	100.0 wt. parts

[0025] A coating liquid was prepared according to the prescription shown in Table 1 above (with the respective components indicated in weight parts). More specifically, into 52.0 wt. parts of 2.3 wt. %-solution in methanol/water of 20 mol. %-saponified polymethyl methacrylate (prepared by dissolving the polymethyl methacrylate in methyl alcohol, followed by addition of sodium hydroxide aqueous solution in an amount sufficient for 20 mol. %-saponification and stirring for 30 min.), 10 %-aqueous solution of polyvinyl alcohol (Dp (average polymerization degree) = 2000, Dsap. (saponification degree) = ca. 82 mol. %) was added, and the resultant mixture was further stirred for 10 min. at room temperature (25 °C), followed by addition of acetylacetone and 15 min. of stirring at room temperature, to prepare a coating liquid.

[0026] The thus-prepared coating liquid was colorless and clear and applied onto a glass sheet of 40 mm x 70 mm x 1 mm(t) at a pulling-up speed of 30 mm/min. by using a dip coater, followed by 10 min. of drying under heating at 100 °C, to provide a uniform, colorless and clear coating film having a thickness of 3.0 µm.

[0027] The coated glass sheet was then stored for 5 min. in a refrigerator (at ca. 0 °C) and then left standing in an environment of 25 °C and 81 % relative humidity, whereby no fog occurred at all on the coated surfaces of the glass sheet. Further, one surface of the coated glass sheet was wiped 20 times with a lens-cleaning paper ("Dasper" (trade name), OZU Co., Ltd., Tokyo) soaked with water under a load of 200 g, whereby the coating film was not peeled off at all or damaged at all.

Comparative Example 1

[0028] A coating liquid was prepared and applied onto a glass sheet in the same manner as in Example 1 except for omitting the addition of the acetylacetone. After the drying and heating, a somewhat turbid coating film was formed in a thickness of 2.8 µm. As a result of the same tests as in Example 1, no fog occurred on the coating film, but the coating film caused peeling-off after ca. 5 times of the wiping.

Example 2

[0029]

(Table 2)

Methyl acrylate/ethyl acrylate/ methacrylic acid (40/40/2 by weight) copolymer ammonium salt (Mw = 12×10^4) (2.5 wt. % solution in water/methanol)	50.0 wt.parts
Polyvinyl alcohol (Dp = 2000, Dsap = ca. 82 mol. %) (10 wt. % aqueous solution)	49.0 wt.parts
Acetylacetone	1.0 wt.part
Total	100.0 wt.parts

[0030] A coating liquid was prepared according to the prescription shown in Table 2 above and applied onto a glass sheet, followed by drying under heating, in the same manner as in Example 1, whereby a uniform, colorless and clear coating film was formed in a thickness of 3.3 µm. As a result of the tests in the same manner as in Example 1, the coating film caused no fog at all on the surface and caused no peeling or damage after the wiping.

Example 3

[0031]

Polymethyl acrylate 20 mol. %-saponified product (Mw = 15×10^4) (2.5 wt. %-solution in water/ methanol)	50.3 wt.parts
Polyvinyl alcohol (Dp = 2000, Dsap = ca. 82 mol. %) (10 wt. %-aqueous solution)	45.7 wt.parts
Sodium silicate ($\text{SiO}_2/\text{Na}_2\text{O} = 3.1$ (by mol) -aqueous solution)	3.1 wt.parts
Acetylacetone	0.9 wt.part
Total	100.0 wt.parts

[0032] A coating liquid was prepared according to the prescription shown in Table 3 above and applied onto a glass sheet, followed by 10 min. of drying under heating at 130 °C, otherwise in the same manner as in Example 1, whereby a uniform, colorless and clear coating film was formed in a thickness of 3.0 µm. As a result of the tests in the same manner as in Example 1, the coating film caused no fog at all on the surface and caused no peeling or damage after

20 times, of wiping with water-soaked lens-cleaning paper.

Claims

1. An anti-fog coating material, comprising: a polyacrylic acid compound, polyvinyl alcohol and acetylacetone.
2. The coating material according to claim 1, further containing a solvent comprising an alcohol and water.
3. The coating material according to claim 1 or claim 2, wherein said polyacrylic acid compound comprises at least one member selected from the group consisting of polyacrylic acid, polymethacrylic acid, polyacrylic acid esters and polymethacrylic acid esters.
4. The coating material according to any one of claims 1 to 3, further containing sodium silicate.
5. An anti-fog article, comprising: a substrate and a coating film formed on the substrate by application of the solution of any of claims 1 to 4.
6. The article of claim 5, which is of glass.
7. The article of claim 5, which is of plastics.
8. The article according to claim 5, 6 or 7 wherein the substrate is a member selected from the group consisting of lenses, optical parallel plates, mirrors and prisms.
9. The article of claim 5 which is of sheet glass.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 30 8280

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.CI.6)
A	PATENT ABSTRACTS OF JAPAN vol. 018, no. 485 (C-1248), 9 September 1994 & JP 06 158031 A (SEKISUI CHEM CO LTD), 7 June 1994 * abstract *	1-9	C09K3/18 C03C17/28
A	PATENT ABSTRACTS OF JAPAN vol. 011, no. 335 (P-632), 4 November 1987 & JP 62 118301 A (NIPPON SHEET GLASS CO LTD), 29 May 1987 * abstract *	1-9	
A	DATABASE WPI Section Ch, Week 8142 Derwent Publications Ltd., London, GB; Class A92, AN 81-76853D XP002090233 & JP 56 112984 A (TANAKA Y) , 5 September 1981 * abstract *	1-9	
A	PATENT ABSTRACTS OF JAPAN vol. 004, no. 155 (C-029), 29 October 1980 & JP 55 099987 A (KANSAI PAINT CO LTD), 30 July 1980 * abstract *	1-9	C09K C03C
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 18 January 1999	Examiner Shade, M
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 01/92 (P4/C01)

need 1-3, 5-12, 14, 16-23
 have 1, 2, 5-10, 12, 14, 16-23
 need 3, 20, 23